

Pietra Blend



Pietra Blend

Available Items



12x24 Grey



12x24 Waves Grey



4x24 Deco Blend Grey



12x24 Pearl



12x24 Waves Pearl



4x24 Deco Blend Pearl



12x24 White



12x24 Waves White



4x24 Deco Blend White

DWDD



DD















DWDD

3x12 Bullnose also available



Pietra Blend

Technical Data

	Spessore	Variatione cromatica	Formatura del prodotto	Assorbimento d'acqua	Carico di rottura	Durezza della superficie	Resistenza agli sbalzi termici	Resistenza al cavillo	Conducibilità Termica	Cessione Piombo Cadmio	Resistenza chimica	PEI Resistenza all'abrasione superficiale	Resistenza al gelo	Coefficiente dinamico di frizione	Resistenza allo scivolamento
	Thickness	Shade variation	Product Moulding	Water absorption	Modulus of rupture	Hardness of the surface	Resistance to thermal shock	Crazing resistance	Electrical Conductivity	Emission Lead Cadmium	Chemical resistance	Resistance to surface abrasion	Frost resistance	Dynamic coefficient of friction	Slip resistance
				ISO 10545-3	ISO 10545-4	E.N. 101 MOHS	ISO 10545-9	ISO 10545-11	UNI EN. 1745	ISO 10545-15	ISO 10545-13	ISO 10545-7	ISO 10545-12	DCOF	DIN 51130 DIN 51097
									CT	Pb / Cd					
Feel	10 mm	V2	RET	< 0,5 % Bla	≥ 43 N/mm ²	-	Garantita Guaranteed	Garantita Guaranteed	0,675 < CT < 0,715 W/mk	Pb < 0,1 Cd < 0,01	GA (M) GLA (M) GHA (M)	5	Garantita Guaranteed	> 0,42	R10 A+B
Feel  Lux	10 mm	V2	RET	< 0,5 % Bla	≥ 43 N/mm ²	4	Garantita Guaranteed	Garantita Guaranteed	0,675 < CT < 0,715 W/mk	Pb < 0,1 Cd < 0,01	-	-	Garantita Guaranteed	-	-
Feel Antislip	10 mm	V2	RET	< 0,5 % Bla	≥ 43 N/mm ²	-	Garantita Guaranteed	Garantita Guaranteed	0,675 < CT < 0,715 W/mk	Pb < 0,1 Cd < 0,01	GA (M) GLA (M) GHA (M)	5	Garantita Guaranteed	> 0,42	R11 A+B+C